

**CF103 TR\***

CF103 TR is a Premium Grade CHEMFAB® PTFE-coated fibreglass fabric that possesses excellent flexibility and crease characteristics.

It is typically used as in applications where an extremely smooth and flexible release fabric is required.

**Typical Properties**

Property	Value	Value	Test Method
Weight	g/m <sup>2</sup>	145	FTMS 191A-5041
Thickness	mm	0.075	FTMS 191A-5030
Tensile Strength	N/cm	110 x 90	FTMS 191A-5102
Trap Tear Strength	N	23 x 17	FTMS 191A-5136
PTFE Content	%	67	-
Temperature Resistance	°C	-150 to +260	-
Standard Width	mm	1000	-

\* Formerly CF 100-3 TRX, Tygaflor 108ATR

**Saint-Gobain Performance Plastics  
Ireland**

Kilrush Business Park,  
Kilrush, Co. Clare, V15 NW27  
Tel: +353 65 90 80 170

**Saint-Gobain Performance Plastics  
Germany**

Tel: +49 (0) 2203 956-362

**Saint-Gobain Performance Plastics  
Tygaflor Ltd  
United Kingdom**

Tel: +44 (0) 1706 746900

**Saint-Gobain Performance Plastics  
Poland**

Tel: +48 (63) 261 7252

[chemfab@saint-gobain.com](mailto:chemfab@saint-gobain.com)

[www.chemfab.com](http://www.chemfab.com)

CHEMFAB® is a registered trademark ©2017 Saint-Gobain Performance Plastics Corporation

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof.

Saint-Gobain Performance Plastics does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s). Nothing in this disclaimer limits Saint-Gobain Performance Plastics' liability for death or personal injury due to its negligence

Valid 03/2017 • Supersedes all previous versions  
PDS.CF103TR.0317.EU.CFMC

