

**CF250 F**

CF250 F was designed as a lightweight CHEMFAB® material that utilizes a tightly woven Beta® fiberglass substrate, lightly coated with PTFE. This product is silicone free.

Because of its minimalistic footprint, ease of hand, chemical inertness and solar properties, CF250 F excels in aerospace applications from space shuttles and international space stations.

**Typical Properties**

Property	Units	Value
Widths Available	inches	51
Weight	oz/yd <sup>2</sup>	3.8
Thickness	inches	~ 4-5
Breaking Strength (Warp)	lbs/in	>65
Breaking Strength (Fill)	lbs/in	>50
Trapezoidal Tear (Warp)	lbs	>2
Trapezoidal Tear (Fill)	lbs	>1
Stiffness	lbs/in	<1
Elongation at Break (Warp)	%	~ 2
Elongation at Break (Fill)	%	~ 2
Thermal Emittance	%	~ >0.88
Solar Absorbance	%	<5
Solar Transmittance	%	<50
Abrasion Resistance	Taber Cycles	>750
Resin Content	%	17-22

**Saint-Gobain Performance Plastics**  
 701 Daniel Webster Highway  
 Merrimack, NH 03054  
 Customer Service: +1 800 451 6101  
 Telephone: +1 603 424 9000

[chemfab@saint-gobain.com](mailto:chemfab@saint-gobain.com)

[www.chemfab.com](http://www.chemfab.com)

Beta® is a registered trademark of Advanced Glassfiber Yarns LLC (AGY).  
 CHEMFAB® is a registered trademark ©2017 Saint-Gobain Performance Plastics Corporation

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Valid 02/2017 • Supersedes all previous versions  
 PDS.CF250F.0217.US.CFMC

