

SP405-2

SP405-2 is a low weight dimensionally stable material with a slightly textured surface to provide grip. It provides some release properties chemical and wear characteristics over wide temperature ranges.

SP405-2 is typically used in convoluted tube or hose manufacturing.

Typical Properties

| Property | Value | Value | Test Method |
|------------------------|------------------|--------------|----------------|
| Weight | g/m ² | 193 | FTMS 191A-5041 |
| Thickness | MM | 0.120 | FTMS 191A-5030 |
| Tensile Strength | N/cm | 260 X 230 | FTMS 191A-5102 |
| Trap Tear Strength | N | 38 X 30 | FTMS 191A-5136 |
| PTFE Content | % | 45.5 | |
| Temperature Resistance | °C | -150 to +260 | |
| Standard Width | mm | 1000 | |

*Your text here

Saint-Gobain Performance Plastics Ireland

Kilrush Business Park,
Kilrush, Co. Clare, V15 NW27
Tel: +353 65 90 80 170

Saint-Gobain Performance Plastics Germany

Tel: +49 (0) 2203 956-362

Saint-Gobain Performance Plastics Tygaflor Ltd United Kingdom

Tel: +44 (0) 1706 746900

Saint-Gobain Performance Plastics Poland

Tel: +48 (63) 261 7252

chemfab@saint-gobain.com
www.chemfab.com

CHEMFAB® is a registered trademark of Saint-Gobain Performance Plastics Corporation
Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. Saint-Gobain Performance Plastics does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s). Nothing in this disclaimer limits Saint-Gobain Performance Plastics' liability for death or personal injury due to its negligence

Valid 03/2017 o Supersedes all previous versions
PDS.CF105-2AS.0317.EU.CFMC

