

CORETECH® Darlyn1100 CB

Darlyn1100 CB is a CORETECH® expansion joint fabric that provides long service life due to its outstanding chemical resistance in harsh conditions and superior strength retention even after repeated flexing.

Commonly used with expansion joints in flue gas desulphurization units, power plants, pulp and paper plants, and similar applications.

Typical Properties

| Property | Imperial Units | SI Units |
|----------------------------------|-----------------------|-----------------------|
| Width | 48, 57 in | 1220, 1450 mm |
| Weight | 72 oz/yd ² | 2440 g/m ² |
| Thickness | 0.056 in | 1.4 mm |
| Breaking Strength Warp, Fill | 1400 lbs/in | 12460 N/cm |
| Trap Tear Strength Warp, Fill | 270 lbf | 1200 N |
| Temperature Resistance | -40 to +500°F | -40 to +260°C |
| Construction | Laminated | |
| Gas Side PTFE Film Color | Orange | |

Saint-Gobain Performance Plastics
701 Daniel Webster Highway
Merrimack, NH 03054
Customer Service: +1 800 451 6101
Telephone: +1 603 424 9000

protectivesystems@saint-gobain.com

www.coretechprotection.com

CORETECH® is a registered trademark ©2017 Saint-Gobain Performance Plastics Corporation

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Valid 06/2017 • Supersedes all previous versions
PDS.CTDARLYN1100CB.0617.US.CFMC

